

Test Report

Photographic Activity Test according to ISO 18916:2007

Summary: The material described below has **passed** the criteria for enclosure materials defined in ISO 18916:2007 "Photographic activity test for enclosure materials".

PTS Test-Report: **32.911**
Material description: **Filmoplast P**

Supplied by: **Neschen AG** on **03.02.2016**
Hans-Neschen-Str. 1, 31675 Bückeburg

Test Results

1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than $\pm 20\%$ compared to the control.

Density change of control: **-1.20**
Density change of material: **-1.17** Relative difference: **3%**

2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: **0.15**
Density change of material: **0.14** Difference: **0.01**

3. Mottle Test

The enclosure material shall not produce *easily recognizable* mottling.

Visual assessment: **Passed**

Date of testing: **12.05.2016** Sample-ID: **007-05**

Papiertechnische Stiftung, Pirnaer Straße 37, D-01809 Heidenau, Germany




Dipl.-Ing. Sabine Pensold
Laboratory Manager Materials Testing


Dr. Carsten Schönfeld
PAT Project Manager